

ANMASI CURATECH PA 6317 Water-based anticorrosion agent

Supplier:
ANMASI A/S
Thorsvej 106
DK-7200 Grindsted

Fields of application:

Passivation of ferrous and non-ferrous metals like copper, brass, nickel and zinc.

Your contact:

Anders Hedeby Sørensen
Tel.: 76 50 02 32
Mail.: ah@anmasi.dk

PRODUCT DESCRIPTION

Product data

Form:	liquid
pH-value:	ca. 4
Colour:	yellow
Density g/cm ³ :	0.99 - 1.03 g/ml
Sensitive to cold below approx. °C:	+5°C

Properties

- The product forms a molecular film on fat-free surfaces.
- After passivation the treated surfaces should be rinsed with water and dried.
- Curatech PA 6317 solutions can be used in plastic – or V4A tanks.
- Passivation of copper, brass and nickel:

Application

Passivation of copper, brass and nickel:

Water	97 up to 99 %
Curatech PA 6317	0.5 up to 1.0 %
Sulfuric acid	0.5 up to 2.0 %

Passivation of iron:

Water	97 up to 99 %
Curatech PA 6317	0.5 up to 1.0 %
Phosphoric acid	0.5 up to 2.0 %

The passivation of zinc, the pH value should not be less than 2.

Temperature

The application temperature should be between 20 - 60 °C.

ACOFT20.08.13

These notes are based on results gained from practical use to the present time. Taking into consideration individual operating conditions, deviations cannot be excluded. For this reason, we do not accept any third-party liability.