

## ANMASI CURATECH TA 279 Liquid, alkaline degreaser containing silicate

### Fields of application:

Product containing silicate for the cleaning of stainless steel, steel, aluminium and non-ferrous metals.

### Supplier:

ANMASI A/S  
Thorsvej 106  
DK-7200 Grindsted

### Your contact:

Anders Hedeby Sørensen  
Tel.: 76 50 02 32  
Mail.: ah@anmasi.dk

## PRODUCT DESCRIPTION

### Product data

Form:	liquid
pH-value:	11,4 – 12,4
Colour:	clear - light yellow
Density g/cm <sup>3</sup> :	1.19 - 1.22 g/ml
Sensitive to cold below approx. °C:	+5°C

### Properties

- Curatech TA 279 can be used both in an immersion process and in a spray process.
- The cleaning performance of Curatech TA 279 is additionally strengthened by special wetting agents.
- Good workshop cleaner for heavy contained parts

### Application

The cleaning temperature in a spray process is between 40 °C and 60 °C.

In the immersion process, a temperature of 65 °C should not be exceeded.

The cleaning time depends on the type and degree of soiling and typically is between 4 and 8 minutes.

### Temperature

Curatech TA 279 is primarily used at a concentration of 3 % to 6 %.

### Compatibility of materials

Chromium nickel steel, regular steel, aluminium, galvanised steel, non-ferrous metal, glass enamel, alkali-resistant plastics

### ACOFT20.08.13

These notes are based on results gained from practical use to the present time. Taking into consideration individual operating conditions, deviations cannot be excluded. For this reason, we do not accept any third-party liability.