

ANMASI CURATECH TN 249 Liquid soak and spray cleaner for all metal surfaces

Supplier:
ANMASI A/S
Thorsvej 106
DK-7200 Grindsted

Your contact:
Anders Hedeby Sørensen
Tel.: 76 50 02 32
Mail.: ah@anmasi.dk

Fields of application:

Silicate-free, neutral product for the cleaning of iron, aluminium, zinc, stainless and non-ferrous metals.

PRODUCT DESCRIPTION

Product data

Form:	liquid
pH-value:	7.0 - 7.5
Colour:	Colourless to white yellow
Density g/cm ³ :	1.57 - 1.61 g/ml
Sensitive to cold below approx. °C:	+5°C

Properties

- Curatech TN 249 can be used both in an immersion process and in a spray process.
- Typically the cleaning performance of Curatech TN 249 is additionally intensified by adding special wetting agents.
- The product is non-foaming and ultra filterable.

Application

Curatech TN 249 is primarily used at concentrations of 4 % to 6 % in combination with appropriate wetting agents.

The wetting agent concentration should be 0.2 to 0.4 %.

Temperature

The application temperature should be between 40 - 80 °C.

Compatibility of materials

Chromium nickel steel, regular steel, aluminium, galvanised steel, non-ferrous metal, glass enamel, alkali-resistant plastics

ACOFT20.08.13

These notes are based on results gained from practical use to the present time. Taking into consideration individual operating conditions, deviations cannot be excluded. For this reason, we do not accept any third-party liability.